

**Aluminized BC Fiberglass Satin
Type: #1018**

Description:	FGB545Satin		
Coating Face:	Gentex Dual Mirror Aluminized Fabric		
Characteristics	Test Method	English	Metric
Areal Weight	ASTM D3776	16.0 oz. / sq. yd.	545 gms. /sq. m.
Thickness	ASTM D1777	0.018 inches	0.46 mm.
Breaking Strength (lbs.)	ASTM D5034		
Warp		550 lbs.	2447 N
Fill		400 lbs.	1780 N
Tear Strength (lbs.)	ASTM D1424		
Warp		CNM lbs.	CNM N
Fill		25 lbs.	111 N
Flame Resistance	ASTM D6413		
After flame		1.0 seconds	1.0 seconds
Char length		0.50 inches	1.3 cm.
Radiant Reflectivity	MIL-C-24929A	10 seconds	10 seconds

TYPE 1018

**DUAL
MIRROR®**

GENTEX®