

Aluminized Korspun I

Production Information: Type: #1081-1

Description:	KOR645Plain-1
Coating Face:	Gentex Dual Mirror Aluminized Fabric Type 1081-1 has a higher glass content than Type 1081

Characteristics	Test Method	English	Metric
Areal Weight	ASTM D3776	19.0 oz. / sq. yd.	645 gms. /sq. m.
Thickness	ASTM D1777	0.045 inches	1.14 mm.
Breaking Strength (lbs.)	ASTM D5034		
Warp		350 lbs.	1557 N
Fill		100 lbs.	445 N
Tear Strength (lbs.)	ASTM D1424		
Warp		CNM	CNM
Fill		20 lbs.	89 N
Flame Resistance	ASTM D6413		
After flame		2.0 seconds	2.0 seconds
Char length		0.5 inches	1.3 cm.
Radiant Reflectivity	MIL-C-24929A	30 seconds	30 seconds

TYPE 1081-1

**DUAL
MIRROR®**

GENTEX®