

**Aluminized Para Aramid Twill
Type: #1091**

Product Information:

Description:	PA375Twill
Coating Face:	Gentex Dual Mirror Aluminized Fabric
Additional Certification:	NFPA 1971 2007 EN531 (Pass A, B1and C4)

Characteristics	Test Method	English	Metric
Areal Weight	ASTM D3776	11 oz./sq .yd.	375 gms./ sq. m.
Thickness	ASTM D1777	0.019 inches	0.48 mm.
Breaking Strength (lbs.)	ASTM D5034		
Warp		550 lbs.	2224 N
Fill		450 lbs.	2002 N
Tear Strength (lbs.)	ASTM D1424		
Warp		50.0 lbs.	222 N
Fill		50.0 lbs.	222 N
Flame Resistance	ASTM D6413		
After flame		2.0 seconds	2.0 seconds
Char length		1.0 inches	2.54 cm.
Radiant Reflectivity	NFPA 1971 2007	30 seconds	30 seconds

DUAL
MIRROR[®]

TYPE 1091

GENTEX[®]