

**Aluminized Meta Aramid Twill
Type: #1056**

Product Information

Description:	MA290Twill
Coating Face:	Gentex Dual Mirror Aluminized Fabric
Additional Certification:	NFPA 1971-2007

Characteristics	Test Method	English	Metric
Areal Weight	ASTM D3776	8.5 oz. / sq. yd.	290 gms. /sq. m.
Thickness	ASTM D1777	0.014 inches	0.36 mm.
Breaking Strength (lbs.)	ASTM D5034		
Warp		250 lbs.	1112 N
Fill		150 lbs.	667 N
Tear Strength (lbs.)	ASTM D1424		
Warp		6.0 lbs.	27 N
Fill		4.0 lbs.	18 N
Flame Resistance	ASTM D6413		
After flame		2.0 seconds	2.0 seconds
Char length		4.0 inches	10 cm.
Radiant Reflectivity	NFPA 1971 2007	20 seconds	20 seconds

TYPE 1056

**DUAL
MIRROR®**

GENTEX®