

**Aluminized PFR Rayon
Type: #1006**

Product Information:

Description:	PFR510Herringbone
Coating Face:	Gentex Dual Mirror Aluminized Fabric
Additional Certification:	

Characteristics	Test Method	English	Metric
Areal Weight	ASTM D3776	15.0 oz. / sq. yd.	510 gms. / sq. m.
Thickness	ASTM D1777	0.025 inches	064 mm.
Breaking Strength	ASTM D5034		
Warp		220 lbs.	979 N
Fill		150 lbs.	667 N
Tear Strength	ASTMD1424		
Warp		15 lbs.	67 N
Fill		15 lbs.	67 N
Flame Resistance	ASTMD6413		
After flame		2.0 seconds	2.0 seconds
Char length		4.0 inches	10 cm.
Radiant Reflectivity	MIL-C-24929A	20 seconds	20 seconds

TYPE 1006

**DUAL
MIRROR®**

GENTEX®