

**Aluminized PFR Rayon
Type: #1019**

Product Information:

Description:	PFR645Basket		
Coating Face:	Gentex Dual Mirror Aluminized Fabric		
Characteristics	Test Method	English	Metric
Areal Weight	ASTM D3776	19.0 oz. / sq. yd.	645 gms. /sq. m.
Thickness	ASTM D1777	0.060 inches	1.52 mm.
Breaking Strength (lbs.)	ASTM D5034		
Warp		350 lbs.	1557 N
Fill		180 lbs.	801 N
Tear Strength (lbs.)	ASTM D1424		
Warp		35 lbs.	156 N
Fill		35 lbs.	156 N
Flame Resistance	ASTM D6413		
After flame		2.0 seconds	2.0 seconds
Char length		3.0 inches	7.6 cm.
Radiant Reflectivity	MIL-C-24929A	25 seconds	25 seconds

TYPE 1019

**DUAL
MIRROR®**

GENTEX®