



## TWT-10 Woven Twill

Test	Score
<b>TPP - NFPA 1971-2000</b>	12.60
<b>Thickness (mls)</b>	37.67
<b>Weight - ASTM D 3776 - oz/yd<sup>2</sup></b>	11.50
<b>Weight - ASTM D 3776 - gm/m<sup>2</sup></b>	390
<b>Martindale Abrasion - ASTM D 4966</b>	40000
<b>VF - After Flame - ASTM D6413-1999</b>	0.00
<b>VF - After Glow - ASTM D6413-1999</b>	0.00
<b>VF - Char Length - ASTM D6413-1999</b>	0.30

	ATPV
<b>Arc Rating (ATPV) - cal/cm<sup>2</sup> - ASTM F1959-1999 Arc Rating</b>	12.6

TPP - Thermal Protective Performance

VF - Vertical Flame