



TWT-10 Woven Twill

Test	Score
TPP - NFPA 1971-2000	12.60
Thickness (mls)	37.67
Weight - ASTM D 3776 - oz/yd²	11.50
Weight - ASTM D 3776 - gm/m²	390
Martindale Abrasion - ASTM D 4966	40000
VF - After Flame - ASTM D6413-1999	0.00
VF - After Glow - ASTM D6413-1999	0.00
VF - Char Length - ASTM D6413-1999	0.30

	ATPV
Arc Rating (ATPV) - cal/cm² - ASTM F1959-1999 Arc Rating	12.6

TPP - Thermal Protective Performance

VF - Vertical Flame