

# TECHNICAL DATA



## Ara-Fill

Width (")	60.0 min.
Weight (osy)	16.0 +/- 2.0
Thickness (")	0.065 +/- 0.020
Heat Resistance BW and AW* 5X	Will not ignite, melt, drip, or separate
Thermal Shrinkage BW and AW* 5X	< 10%
Flame Resistance (ASTM D 6413) BW and AW 5X	< 2 sec afterflame and < 4 inch char length

\*AW - wash dry cycles according to AATCC 135 1, V, Ai (Cotton Sturdy)

To the best of our knowledge, the information contained herein is accurate. However, TenCate assumes no liability whatsoever for the accuracy or completeness on the information contained herein. Users must satisfy themselves that the recommendations are suitable for their use and meet all appropriate safety and health standards.