



MAURITZON INC.
ESTABLISHED 1888

CH GRADE SILICA FABRICS

Part# 84-CH; 136-CH; 150-CH; 188-CH.

Product Description

There are four satin weave silica fabrics from which to choose that can withstand molten metal temperatures and offer protection at **continuous temperatures up to 1,800°F (1,000°C)**. All fabrics can be used or fabricated as **welding drop cloths, stress relief blankets, protective screens/covers, furnace curtains, insulation mats and cable tray wraps**. It depends upon the weight/thickness/strength factors as to the fabric that is the best cost effective choice.

Technical Data

<u>Properties(Nominal)</u>	<u>Siltemp 84CH</u>	<u>Siltemp 188CH</u>		
Silicon Dioxide Content	96		96	
Weight, oz/yd (gms./m)	18 (610)		37.5 (1,270)	
Thickness, in. (mm)	0.027 (0.70)	0.054 (1.40)	Tensile, lbs/in	
Warp	220	280	300	330
Fill	110	160	190	200

Notes:

1. Roll length is 50 yards, and roll width is 36.25 inches (920mm). Other roll lengths are available.
2. Siltemp fabrics can meet Military Specs MIL-C-24576A and MIL-I-24244C upon request.
3. A light hydrocarbon coating is applied for improved handling at low temperatures.
4. Siltemp fabrics are amorphous silica textiles, and contain no asbestos or ceramic fibers.

To the best of our knowledge, the information contained herein is accurate. The information provided is based upon data furnished by our suppliers. However, Mauritzon Inc. assumes no liability whatsoever for the accuracy or completeness of the information contained herein. While believed to be reliable, the information of products are intended for use by skilled persons at their own risk. Final determination of suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards that exist.